



STANBRIDGE REUSABLE BEDPANS

TECHNICAL DATA

Material: Prime 3000TF2.5 is a mineral filled copolymer Polypropylene that offers very high stiffness when rigidity is important. Prime 3000TF2.5 has a very low C.L.T.E., excellent cold temperature impact, UV protection, improved rigidity and has high chemical resistance.



PROPERTY	UNIT		ISO	VALUE
PHYSICAL				
Density	g/cc		1183	1.08
Shrinkage	%			0.8-1.0
Melt Flow (230°C/2.16kg)	g/10min		1133	0.5
MECHANICAL				
Strength at Yield	MPa	5.0mm/min	527	26
Ultimate elongation	%	5.0mm/min	527	4.5 - 5.0
Flexural Modulus	MPa		178	3000
Charpy Impact, notched	kJ/m2	23°C	180/A	26
		-20°C		3.5
THERMAL				
HDT@0.45MPa	°C		75	128
CLTE(-30°C to 100°C)	mm/mm/°C		ASTM E831	0.00006
FLAMMABILITY RATING				
Horizontal burn	1.5mm+		UL94	HB

FINISHING

Aluminium tool construction is recommended with a temperature control function to ensure consistent moulding & finished part dimensional tolerances. A constant tool temperature (typically 75°C for PRIME 3000TF2.5) should be maintained throughout the production run. Cooling using air or water spray will speed up the cooling cycle to provide efficient production output.

Once removed from the tool, it is recommended that the component is clamped in a frame for a short period to optimise dimensional stability & reduce the risk of warping. Shrinkage rates are available on application.

Stanbridge Limited Unit 78, Powder Mill Road, Questor Park, Dartford, Kent DA1 1JA

Telephone: +44 (0) 1689 806500

Email: admin@stanbridge.co.uk www.stanbridge.co.uk

Registered in England and Wales No. 570388 Registered Office: as above

VAT No. 335 8708 35





COLOUR, TEXTURES, CAPABILITIES

PRIME 3000TF2.5 is available in a full range of colours (subject to minimum order quantities) either colour matched to specific colour references, or to customer sample. A range of more standard colours is available for non-specific requirements. PRIME 3000TF2.5 is available with a smooth or with a textured finish. Emboss swatches are available on request.

Notice: All statements, information, and data given herein are believed to be accurate and reliable but are presented without guarantee, warranty, or responsibility of any kind, expressed or implied. Statements or suggestion concerning possible use of our products are made without presentation of warranty that such use is free of patent infringement and are not recommendations to infringe any patent. The user should not assume that all safety measures are indicated or that other measures may not be required.